


REPORT

TRUESDAIL LABORATORIES, INC.



CHEMISTS - MICROBIOLOGISTS - ENGINEERS
RESEARCH - DEVELOPMENT - TESTING

14201 FRANKLIN AVENUE
TUSTIN, CALIF. 92680
AREA CODE 714 • 730-6239
AREA CODE 213 • 225-1564
FAX 714 • 730-6462

General Chemical Corp.
P.O.Box 1697
Chino, California 91708
Attn: Robert Munion

DATE: Dec. 12, 1990

RECEIVED: Dec. 3, 1990

LABORATORY NO: 40515

2 Quart Bottles of "BIG BLUE - Low Temp."

Testing as Requested

<u>DETERMINATION</u>	<u>METHOD</u>	<u>RESULTS</u>
Corrosivity	EPA 1110	0.14 mm ^{py} *
Oxygen Compatability	Provided Procedure	Pass

* mm^{py} = millimeters per year

Note: The maximum temperature rise during the 30 minute test period for the air was 0.20°C and for the oxygen was 0.58°C.

Respectfully Submitted.

TRUESDAIL LABORATORIES, INC.

David A. Stivers, Manager
General Chemistry



This report applies only to the sample, or samples, investigated and is not necessarily indicative of the quality or condition of apparently identical or similar products. As a mutual protection to clients, the public and these Laboratories, this report is submitted and accepted for the exclusive use of the client to whom it is addressed and upon the condition that it is not to be used, in whole or in part, in any advertising or publicity matter without prior written authorization from these Laboratories.