

SUBMITTAL RECORD _____
 JOB _____
 LOCATION _____
 SUBMITTED TO _____
 SUBMITTAL PREPARED BY _____
 APPROVED BY _____
 DATE _____




Submittal Form DN/UVDN Dyn-O-Tie®

DESCRIPTION


Whenever your job calls for securing round flexible duct to outlets, pipes or fittings, you can do the job better, faster, and at a lower cost using DYN-O-TIES, flexible duct ties. DYN-O-TIES, when properly installed, provide a secure connection of flexible duct listed by Underwriters Laboratories Inc., class 1. UV Resistant DYN-O-TIES are made to resist Ultraviolet rays and adverse weather conditions when used in outdoor applications.

STORAGE

To ensure superior performance, nylon cable tie products should be stored in a sealed polyethylene bag at room temperature in at least 50% humidity (recommended 80% RH). Limit the exposure of unused cable ties to extreme heat and cold. Should cable ties be exposed to extreme temperatures and/or extreme relative humidity, store at room temperature and at least 50% humidity (recommended 80% RH) for at least 24 hrs in a sealed bag prior to further use.



NYLON
6/6 V2 – available in five sizes
Self-extinguishing
Fungus inert
Normal service temp. range: – 40° F to 185° F
Test Results*: Nylon -175 lbs.



Tape and mastic products covered under this category investigated to ANSI/UL 181A, “Closure Systems for Use with Rigid Air Ducts and Air Connectors,” or ANSI/UL 181B, “Closure Systems for Use with Flexible Air Ducts and Air Connectors,” have also been tested to ANSI/UL 723, “Test for Surface Burning Characteristics of Building Materials.” Mechanical fasteners covered under this category investigated to ANSI/UL 181B have also been tested to ANSI/UL 2043, “Fire Test for Heat and Visible Smoke Release for Discrete Products and Their Accessories Installed in Air-Handling Spaces.” These products have been found to be suitable for use in plenums in accordance with the “International Mechanical Code,” “Uniform Mechanical Code,” and ANSI/NFPA 90A, “Installation of Air-Conditioning and Ventilating Systems.”



*Note: Ties are tested to CSA C22.2NO.18.5-02 / UL 1565. Test Method: Tie is secured at both ends forming a loop. A weight is suspended from the bottom of loop to determine tensile strength of DYN-O-TIE strap.

ITEM #	CODE	DESCRIPTION	COLOR	LENGTH	MAX. DIA.	PACKAGING	PKG./CTN
7002	UVDN48	UV Resistant Nylon - Imported	Black	48”	14”	50	10
7003	UVDN36	UV Resistant Nylon - Imported	Black	36”	11”	50	10
7004	DN36N	Nylon - Imported	Natural	36”	11”	50	10
7005	DN48N	Nylon - Imported	Natural	48”	14”	50	10

Duro Dyne National Corporate Headquarters, Bay Shore, NY
 631-249-9000 • Fax: 631-249-8346
 Duro Dyne Midwest • Duro Dyne West • Duro Dyne Canada
 www.durodyne.com • E-mail: durodyne@durodyne.com



Duro Dyne Corporation
 Printed in USA 6/30/2022
 BO008467